

DRJ Cross-Laminated Timber
D.R. Johnson Wood Innovations

PR-L320
Revised May 4, 2020

Products: DRJ Cross-Laminated Timber
D.R. Johnson Wood Innovations, 1991 Pruner Road, P.O. Box 66, Riddle, OR 97469
(541) 874-2231
www.drjwoodinnovations.com

1. Basis of the product report:
 - 2018 and 2015 International Building Code (IBC): Section 2303.1.4 Structural glued cross-laminated timber
 - 2012 IBC: Section 104.11 Alternative materials
 - 2018 and 2015 International Residential Code (IRC): Sections R502.1.6, R602.1.6, and R802.1.6 Cross-laminated timber
 - 2012 IRC: Section R104.11 Alternative materials
 - ANSI/APA PRG 320-2019 Performance Rated Cross-Laminated Timber
 - ANSI/APA PRG 320-2017, PRG 320-2012, and PRG 320-2011 Performance Rated Cross-Laminated Timber, recognized in the 2018 IBC and IRC, 2015 IRC, and 2015 IBC, respectively
 - APA Reports T2015P-27, T2017P-01, T2019P-53, and T2020P-15, and other qualification data
2. Product description:

DRJ cross-laminated timber (CLT) is manufactured with Douglas fir-Larch lumber in accordance with ANSI/APA PRG 320 through product qualification and/or mathematical models using principles of engineering mechanics. Allowable design properties for lumber laminations used in DRJ CLT are provided in Table 1. DRJ CLT is permitted for use in floor, roof, and wall applications, and is manufactured with nominal widths of 12 to 120 inches, thicknesses of 3-3/8 to 9-5/8 inches, and lengths up to 42 feet.
3. Design properties:

DRJ CLT shall be designed with the design properties and capacities provided in Tables 2 and 3. The design adjustment factors shall be based on Chapter 10 of the 2018 National Design Specification for Wood Construction (NDS) and approved by the engineer of record. The lateral resistance of DRJ CLT, when used as shearwalls or diaphragms, depends on the panel-to-panel connection and anchorage designs, and shall be consulted with the CLT manufacturer and approved by the engineer of record.
4. Product installation:

DRJ CLT shall be installed in accordance with the recommendations provided by the manufacturer (www.drjwoodinnovations.com) and the engineering drawing approved by the engineer of record. Permissible details shall be in accordance with the engineering drawing.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above). Procedures specified in Chapter 16 of the 2018 NDS shall be permitted for use in designing DRJ CLT for a fire exposure up to 2 hours.
6. Limitations:
 - a) DRJ CLT shall be designed in accordance with principles of mechanics using the design properties specified in this report or provided by the manufacturer.

- b) DRJ CLT products shall be limited to dry service conditions where the average equilibrium moisture content of solid-sawn lumber is less than 16 percent.
 - c) Design properties for DRJ CLT, when used as beams or lintels with loads applied parallel to the face-bond gluelines, are beyond the scope of this report.
 - d) DRJ CLT shall be manufactured in accordance with ANSI/APA PRG 320 for the grades and layups specified in this report and documented in the D.R. Johnson Wood Innovations' in-plant manufacturing standard approved by APA.
 - e) DRJ CLT is produced at the facilities of D.R. Johnson Wood Innovations, Riddle, Oregon, under a quality assurance program audited by APA.
 - f) This report is subject to re-examination in one year.
7. Identification:
DRJ CLT described in this report is identified by a label bearing the manufacturer's name (D.R. Johnson Wood Innovations) and/or trademark, the APA assigned plant number (1117), the product standard (ANSI/APA PRG 320), the APA logo, the CLT grade, the report number PR-L320, and a means of identifying the date of manufacture.

Table 1. ASD Reference Design Values^(a) for Lumber Laminations Used in DRJ CLT (for Use in the U.S.)

CLT Grade	Laminations Used in Major Strength Direction							Laminations Used in Minor Strength Direction						
	Grade & Species	F _b (psi)	E (10 ⁶ psi)	F _t (psi)	F _c (psi)	F _v (psi)	F _s (psi)	Grade & Species	F _b (psi)	E (10 ⁶ psi)	F _t (psi)	F _c (psi)	F _v (psi)	F _s (psi)
E2, E2.1	1650f-1.5E DF	1,650	1.5	1,020	1,700	180	60	No. 3 DF	525	1.4	325	775	180	60
E2M1	2250F _b -2.0E-1600F _t DF	2,250	2.0	1,600	1,925	180	60	2250F _b -2.0E-1600F _t DF	2,250	2.0	1,600	1,925	180	60
E2M3, E2M3.1	2250F _b -2.0E-1600F _t DF	2,250	2.0	1,600	1,925	180	60	No. 2 DF	900	1.6	575	1,350	180	60
E2M4, E2M4.1	2250F _b -2.0E-1600F _t DF	2,250	2.0	1,600	1,925	180	60	No. 3 DF	525	1.4	325	775	180	60
V1, V1.1	No. 2 DF	900	1.6	575	1,350	180	60	No. 3 DF	525	1.4	325	775	180	60
V1M1, V1M1.1	No. 2 DF	900	1.6	575	1,350	180	60	No. 2 DF	900	1.6	575	1,350	180	60

For SI: 1 psi = 0.006895 MPa

^(a) Tabulated values are allowable design values and not permitted to be increased for the lumber flat use or size factor in accordance with the NDS. The design values shall be used in conjunction with the section properties provided by the CLT manufacturer based on the actual layup used in manufacturing the CLT panel (see Table 2).

Table 2. ASD Reference Design Values^(a) for DRJ CLT (for Use in the U.S.)

CLT Grade ^(b)	Layup ID ^(c)	Thick-ness, t_p (in.)	Lamination Thickness (in.) in CLT Layup							Major Strength Direction				Minor Strength Direction			
			=	⊥	=	⊥	=	⊥	=	(F_bS) _{eff,f,0} (lb-ft ² /ft)	(EI) _{eff,f,0} (10 ⁶ lb-ft ² /ft)	(GA) _{eff,f,0} (10 ⁶ lb/ft)	$V_{s,0}$ (lb/ft)	(F_bS) _{eff,f,90} (lb-ft ² /ft)	(EI) _{eff,f,90} (10 ⁶ lb-ft ² /ft)	(GA) _{eff,f,90} (10 ⁶ lb/ft)	$V_{s,90}$ (lb/ft)
E2	3	4 1/8	1 3/8	1 3/8	1 3/8					3,825	102	0.53	1,980	165	3.6	0.56	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			8,825	389	1.1	3,300	1,440	95	1.1	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	15,600	963	1.6	4,625	3,300	364	1.7	3,300
E2.1	3	3 3/8	1 3/8	5/8	1 3/8					2,650	57	0.56	1,620	35	0.34	0.31	300
	5	5 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8			6,100	210	1.1	2,575	520	22	0.62	1,260
	7	7 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5/8	1 3/8	10,850	513	1.7	3,550	1,170	87	0.94	2,220
E2M1	3	4 1/8	1 3/8	1 3/8	1 3/8					5,225	135	0.75	1,980	710	5.2	0.75	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			12,025	519	1.5	3,300	6,150	135	1.5	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	21,300	1,286	2.2	4,625	14,150	519	2.3	3,300
E2M3	3	4 1/8	1 3/8	1 3/8	1 3/8					5,225	135	0.61	1,980	285	4.2	0.73	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			12,025	518	1.2	3,300	2,460	108	1.5	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	21,225	1,282	1.8	4,625	5,675	416	2.2	3,300
E2M3.1	3	3 3/8	1 3/8	5/8	1 3/8					3,600	76	0.65	1,620	60	0.39	0.41	300
	5	5 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8			8,325	280	1.3	2,575	890	25	0.83	1,260
	7	7 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5/8	1 3/8	14,775	684	2.0	3,550	2,020	100	1.2	2,220
E2M4	3	4 1/8	1 3/8	1 3/8	1 3/8					5,225	135	0.54	1,980	165	3.6	0.72	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			12,000	518	1.1	3,300	1,440	95	1.4	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	21,200	1,281	1.6	4,625	3,325	365	2.2	3,300
E2M4.1	3	3 3/8	1 3/8	5/8	1 3/8					3,600	76	0.58	1,620	35	0.34	0.41	300
	5	5 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8			8,300	280	1.2	2,575	520	22	0.82	1,260
	7	7 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5/8	1 3/8	14,775	684	1.7	3,550	1,180	88	1.2	2,220
V1	3	4 1/8	1 3/8	1 3/8	1 3/8					2,090	108	0.53	1,980	165	3.6	0.59	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			4,800	415	1.1	3,300	1,440	95	1.2	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	8,500	1,027	1.6	4,625	3,300	364	1.8	3,300
V1.1	3	3 3/8	1 3/8	5/8	1 3/8					1,440	61	0.56	1,620	35	0.34	0.33	300
	5	5 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8			3,325	224	1.1	2,575	520	22	0.66	1,260
	7	7 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5,925	547	1.7	3,550	1,180	87	1.0	2,220

(Footnotes on the following page)

Table 2. ASD Reference Design Values^(a) for DRJ CLT (for Use in the U.S.) (Continues)

CLT Grade ^(b)	Layup ID ^(c)	Thick-ness, t_p (in.)	Lamination Thickness (in.) in CLT Layup							Major Strength Direction				Minor Strength Direction			
			=	⊥	=	⊥	=	⊥	=	$(F_bS)_{eff,f,0}$ (lbf-ft/ft)	$(EI)_{eff,f,0}$ (10^6 lbf-in. ² /ft)	$(GA)_{eff,f,0}$ (10^6 lbf/ft)	$V_{s,0}$ (lbf/ft)	$(F_bS)_{eff,f,90}$ (lbf-ft/ft)	$(EI)_{eff,f,90}$ (10^6 lbf-in. ² /ft)	$(GA)_{eff,f,90}$ (10^6 lbf/ft)	$V_{s,90}$ (lbf/ft)
V1M1	3	4 1/8	1 3/8	1 3/8	1 3/8					2,090	108	0.60	1,980	285	4.2	0.60	660
	5	6 7/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8			4,825	415	1.2	3,300	2,460	108	1.2	1,980
	7	9 5/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	1 3/8	8,525	1,029	1.8	4,625	5,675	415	1.8	3,300
V1M1.1	3	3 3/8	1 3/8	5/8	1 3/8					1,440	61	0.63	1,620	60	0.39	0.33	300
	5	5 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8			3,325	225	1.3	2,575	890	25	0.67	1,260
	7	7 3/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5/8	1 3/8	5,925	548	1.9	3,550	2,010	99	1.0	2,220

For SI: 1 in. = 25.4 mm; 1 ft = 304.8 mm; 1 lbf = 4.448N

- (a) Tabulated values are allowable design values and not permitted to be increased for the lumber flat use or size factor in accordance with the NDS.
- (b) The CLT grades are developed based on ANSI/APA PRG 320, as permitted by the standard.
- (c) The layup identification (ID) refers to the number of layers.

Table 3. ASD Reference Design Values^(a) for In-Plane Shear of DRJ CLT (for Use in the U.S.)

CLT Grade	Layup ID	Thickness, t_p (in.)	In-Plane Shear Stress		In-Plane Shear Capacity ^(b)	
			$F_{v,e,0}$ (psi)	$F_{v,e,90}$ (psi)	$F_{v,e,0} t_p$ (lbf/ft of width)	$F_{v,e,90} t_p$ (lbf/ft of width)
E2	3	4 1/8	210 ^(c)	210 ^(c)	10,400 ^(c)	10,400 ^(c)
	5	6 7/8	210 ^(d)	210 ^(d)	17,300 ^(d)	17,300 ^(d)
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)
E2M1	3	4 1/8	210 ^(c)	210 ^(c)	10,400 ^(c)	10,400 ^(c)
	5	6 7/8	210 ^(d)	210 ^(d)	17,300 ^(d)	17,300 ^(d)
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)
E2M3	3	4 1/8	210 ^(c)	210 ^(c)	10,400 ^(c)	10,400 ^(c)
	5	6 7/8	210 ^(d)	210 ^(d)	17,300 ^(d)	17,300 ^(d)
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)
E2M4	3	4 1/8	210 ^(c)	210 ^(c)	10,400 ^(c)	10,400 ^(c)
	5	6 7/8	210 ^(d)	210 ^(d)	17,300 ^(d)	17,300 ^(d)
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)
V1	3	4 1/8	210	210	10,400	10,400
	5	6 7/8	210	210	17,300	17,300
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)
V1M1	3	4 1/8	210 ^(c)	210 ^(c)	10,400 ^(c)	10,400 ^(c)
	5	6 7/8	210 ^(d)	210 ^(d)	17,300 ^(d)	17,300 ^(d)
	7	9 5/8	210 ^(d)	210 ^(d)	24,300 ^(d)	24,300 ^(d)

For SI: 1 psi = 0.006895 MPa

- ^(a) The tabulated values are allowable design values.
- ^(b) The tabulated values are for the full thickness (t_p) of the CLT. The values shall be reduced when the CLT panel thickness is less than the full thickness.
- ^(c) Based on test results from 4-1/8-inch V1 grade CLT.
- ^(d) Based on test results from 6-7/8-inch V1 grade CLT.

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 ▪ *E-mail Address:* help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.